

### General Description

Glass fiber mesh fabrics combined with specially designed mesh surface treatments can be used in a wide range of applications.

Armouring mesh R 267 is specially designed to reinforce areas exposed to increased stress, especially a plinth. Particular fabrics construction supported by special finishing meets the highest requirements in terms of strength and force absorption. Can be used both as a substitute for and in addition to other facade fabrics.

### Technical characteristics

Works Standard: 0326 Glass Fibre Mesh Fabrics

Characteristics	Units Description	R 267 A101	
		Warp	Weft
Square Dimension	mm / informative value	8,5	6,5
Standard Width (1)	cm / individual value	100	
Roll Length (1)	m / individual value	100	
Treated Fabric Thickness	mm / informative value	0,95	
Loom state Fabric Weight	g/m <sup>2</sup> / informative value	267	
Treated Fabric Weight	g/m <sup>2</sup> individual value, minimum	314	
Treatment type	alkaliresistant without emollient, obstructing yarn drifting		

(1) Other dimension on request

Tensile strength (TS) and elongation:

Minimum individual tensile strength (N/50 mm) and maximum elongation (%) when reaching minimum tensile strength is ascertained according DIN EN ISO 13934-1 as per below.

	Tensile Strength		Elongation
	Nominal value	Individual value	Average value
Deposition method			
Standard condition	2000 / 6000	1500 / 5500	4,0 / 4,0
Fast Test (6 hours)	1100 / 4000	1000 / 3800	3,5 / 3,5

### Additional Information

- **Quality inspection**  
The way of quality inspection, taking of the samples and taking over of the material, is according to 0326 works standard
- **Packing:**  
The rolls of fabrics are packed vertically in cardboard, on a wooden pallet. A precise method of packing is mentioned in the works standard for packing
- **Storing:**  
Packed rolls are to be stored in dry rooms. Storing temperature is from -10°C to + 50°C

### Technical Data Sheet

#### Properties

- Protect damage-risk areas
- Improves an impact resistance
- Reliable reinforcement for external facades



Edited by:

**ADFORS Construction Products Europe**

SAINT-GOBAIN ADFORS CZ s.r.o.  
Sokolovska 106  
CZ – 570 21 Litomyšl  
Tel: + 420 461 651 111  
Fax: + 420 461 612 769  
www.sg-adfors.com

**ADFORS Construction Products Europe** reserves the right to change the information given herein without prior notice

Technical Data Sheet N° 45

Last update: 10/09/2012