

General Description

ADFORS GlasGrid CompoGrid Pavement Reinforcement System and Moisture Barrier System is manufactured at a Saint-Gobain ADFORS facility that has achieved ISO 9001:2015 certification and meets the requirements of EN 15381. CompoGrid is a composite material consisting of fiberglass reinforcement grid coated in a patented elastomeric polymer, bonded to a non-woven paving geotextile. The non-woven geotextile is a staple fiber, needlepunched and manufactured from fibers that are needed to form a stable network and retain dimensional stability relative to each other. CompoGrid is resistant to ultraviolet degradation and to biological and chemical environments normally found in soils. CompoGrid conforms to the property values listed below, which have been derived from quality conformance testing performed by an accredited laboratory:

Technical Characteristics

Property	CG 50	CG 100	CG 200	Test Method
Tensile Strength (MD x XD) Ultimate	(55 x 55) - 5 kN/m	(115 x 115) - 15 kN/m	(115 x 215) - 15 kN/m	EN ISO 10319 ASTM D6637
Tensile Elongation Ultimate	2,5 ± 0,5 %	2,5 ± 0,5 %	2,5 ± 0,5 %	EN ISO 10319 ASTM D6637
Tensile Resistance @ 2% Strain (MD x XD)	(46 x 46) ± 10 kN/m	(95 x 95) ± 20 kN/m	(95 x 180) ± 20 kN/m	EN ISO 10319 ASTM D6637
Secant Stiffness EA @ 1% Strain (MD x XD)	(2.200 x 2.200) ± 200 N/mm	(4.600 x 4.600) ± 600 N/mm	(4.600 x 8.600) ± 600 N/mm	EN ISO 10319 ASTM D6637
Young's Modulus E	73.000 MPa	73.000 MPa	73.000 MPa	
Mass per Unit Area	335 g/m ²	535 g/m ²	733 g/m ²	EN ISO 9864 ASTM D5261
Melting Point Coating Melting Point Glass	>232 °C >820 °C	>232 °C >820 °C	>232 °C >820 °C	ASTM D276/EN ISO 3146 ASTM C338
Roll Length	100 m	70 m	60 m	
Roll Width	1,0; 1,5; 2,0; 3,0 m	1,0; 1,5; 2,0; 3,0 m	1,5 m	
Roll Area	100, 150, 200, 300 m ²	70, 105, 140, 210 m ²	90 m ²	
Grid Size (Center to Center of Strand)	25 x 25 mm	25 x 25 mm	25 x 19 mm	
Material	Fiberglass reinforcement with modified polymer coating bonded to a non-woven textile specifically engineered for asphalt overlays.			

Properties

- High grid stiffness provides a wrinkle-free installation and a direct load transmission.
- Low elongation
- Thermal and chemical stability
- Excellent milling performance



The values and tolerances given are obtained in our laboratories and in accredited testing institutions. The information given in this data sheet is to the best of our knowledge true and correct. However new research and practical experience can make revisions necessary. We reserve the right to make changes at any time. Statements concerning possible use of our product are not intended as recommendations for their use in the infringement of any patent. No patent warranty of any kind, expressed or implied, is made or intended.

Installation

- CompoGrid can be installed on an old asphalt surface or evenly milled surface. Fill cracks and depressions wider than 6 mm. Road surface must be dry, clean and dust-free with temperature 5 ° - 60 °C.
- Apply tack coat per project requirements. (See application tack coat rate formula in Installation manual page 3).
- Unroll the geogrid with the non-woven fabric side face down immediately after tack coat spraying. Respect the overlap of end roll joints 10 - 15 cm and longitudinal joints at minimum 5 cm. Ensure sufficient amount of tack is applied at the overlap, in order that both layers of materials become fully saturated.
- Press the grid to a layer to ensure a saturation of bitumen into the fabric.
- Permit the tack to completely cure prior to proceeding.
- Apply asphalt over layer.

See document Installation Procedures for detailed steps available on our website or watch the video on YOUTUBE ADFORS TV channel.



Benefits

- Universal application on milling surface or over existing pavement surfaces
- Quick and efficient installation
- Efficient moisture barrier due to the non-woven fabrics
- High grid stiffness providing a wrinkle free installation
- Easy cutting
- Good trafficability (suppliers, trucks, paver)
- Thermal and chemical stability
- Excellent milling performance
- Measured unlimited recyclability & enhanced properties in Reclaimed Asphalt Pavement (RAP)



Palletization

Product	Roll width	Roll area	Roll weight	Core inner diameter	No of rolls on pallet	Total area
CG50	1 m	100 m ²	36 kg	76 mm	12	1 200 m ²
	1,5 m	150 m ²	53 kg	76 mm	12	1 800 m ²
	2 m	200 m ²	72 kg	76 mm	6	1 200 m ²
	2 m	200 m ²	72 kg	76 mm	10	2 000 m ²
	3 m	300 m ²	108 kg	100 mm	6	1 800 m ²
	3 m	300 m ²	108 kg	100 mm	10	3 000 m ²
CG100	1 m	70 m ²	40 kg	76 mm	12	840 m ²
	1,5 m	105 m ²	59 kg	76 mm	12	1 260 m ²
	2 m	140 m ²	80 kg	76 mm	6	840 m ²
	2 m	140 m ²	80 kg	76 mm	10	1 400 m ²
	3 m	210 m ²	120 kg	100 mm	6	1 260 m ²
	3 m	210 m ²	120 kg	100 mm	10	2 100 m ²
CG200	1,5 m	90 m ²	72 kg	76 mm	12	1 080 m ²




SAINT-GOBAIN ADFORS CZ s.r.o.
 Sokolovská 106
 570 01 Litomyšl
 Czech Republic
 Tel: +420 461 651 111
glasgrid.eu@saint-gobain.com
www.adfors.com

In as much as Saint-Gobain ADFORS has no control over installation design, installation workmanship, accessory materials, or conditions of application, Saint-Gobain ADFORS does not warrant the performance or results of any installation or use of ADFORS GlasGrid CG. This warranty disclaimer includes all implied warranties, statutory or otherwise, including the warranty of merchantability and of fitness for a particular purpose. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product for the particular purpose desired in any given situation.

CE Plant Litomyšl (CZ):
 1021-CPR-040/15-1
 15

ADFORS GlasGrid® is manufactured at an ISO 9001:2015 registered facility of Saint-Gobain ADFORS. ADFORS GlasGrid® is a registered trademark of Saint-Gobain ADFORS. U.S. Patent 8,038,364; 8,349,431 and 8,882,385. Additional patents pending.
 © 2019 Saint-Gobain ADFORS

TROUBLE WITH YOUR ROAD?
 Try the GlasGrid app to fix it!



